

Supplemental
Notice of Allowability

Application No.

09/130,545

Examiner

Terrel Morris

Applicant(s)

CHEN, JOHN YOUNGTU

Art Unit

1771

-- The MAILING DATE of this communication appears on the cover sheet with the correspondence address--

All claims being allowable, PROSECUTION ON THE MERITS IS (OR REMAINS) CLOSED in this application. If not included herewith (or previously mailed), a Notice of Allowance (PTOL-85) or other appropriate communication will be mailed in due course. **THIS NOTICE OF ALLOWABILITY IS NOT A GRANT OF PATENT RIGHTS.** This application is subject to withdrawal from issue at the initiative of the Office or upon petition by the applicant. See 37 CFR 1.313 and MPEP 1308.

1. ☒ This communication is responsive to the communication filed Jan 4, 2002.
2. ☒ The allowed claim(s) is/are 1-4, 7 and 8.
3. ☒ The drawings filed on 04 January 2002 are accepted by the Examiner.
4. ☐ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).
 - a) ☐ All b) ☐ Some* c) ☐ None of the:
 1. ☐ Certified copies of the priority documents have been received.
 2. ☐ Certified copies of the priority documents have been received in Application No. _____.
 3. ☐ Copies of the certified copies of the priority documents have been received in this national stage application from the International Bureau (PCT Rule 17.2(a)).
- * Certified copies not received: _____.
5. ☐ Acknowledgment is made of a claim for domestic priority under 35 U.S.C. § 119(e) (to a provisional application).
 - (a) ☐ The translation of the foreign language provisional application has been received.
6. ☐ Acknowledgment is made of a claim for domestic priority under 35 U.S.C. §§ 120 and/or 121.

Applicant has THREE MONTHS FROM THE "MAILING DATE" of this communication to file a reply complying with the requirements noted below. Failure to timely comply will result in ABANDONMENT of this application. **THIS THREE-MONTH PERIOD IS NOT EXTENDABLE**

7. ☐ A SUBSTITUTE OATH OR DECLARATION must be submitted. Note the attached EXAMINER'S AMENDMENT or NOTICE OF INFORMAL PATENT APPLICATION (PTO-152) which gives reason(s) why the oath or declaration is deficient.
8. ☐ CORRECTED DRAWINGS must be submitted.
 - (a) ☐ including changes required by the Notice of Draftsperson's Patent Drawing Review (PTO-948) attached
 - 1) ☐ hereto or 2) ☐ to Paper No. _____.
 - (b) ☐ including changes required by the proposed drawing correction filed _____, which has been approved by the Examiner.
 - (c) ☐ including changes required by the attached Examiner's Amendment / Comment or in the Office action of Paper No. _____.

Identifying indicia such as the application number (see 37 CFR 1.84(c)) should be written on the drawings in the top margin (not the back) of each sheet. The drawings should be filed as a separate paper with a transmittal letter addressed to the Official Draftsperson.

9. ☐ DEPOSIT OF and/or INFORMATION about the deposit of BIOLOGICAL MATERIAL must be submitted. Note the attached Examiner's comment regarding REQUIREMENT FOR THE DEPOSIT OF BIOLOGICAL MATERIAL.

Attachment(s)

- | | |
|--|--|
| <input type="checkbox"/> Notice of References Cited (PTO-892) | <input type="checkbox"/> Notice of Informal Patent Application (PTO-152) |
| <input type="checkbox"/> Notice of Draftsperson's Patent Drawing Review (PTO-948) | <input type="checkbox"/> Interview Summary (PTO-413), Paper No. _____. |
| <input type="checkbox"/> Information Disclosure Statements (PTO-1449), Paper No. _____. | <input checked="" type="checkbox"/> Examiner's Amendment/Comment |
| <input type="checkbox"/> Examiner's Comment Regarding Requirement for Deposit of Biological Material | <input type="checkbox"/> Examiner's Statement of Reasons for Allowance |
| | <input type="checkbox"/> Other |


Applicant's Amendment

1. Applicant's substitute specification filed January 4, 2002 will not be entered for the following reasons:

- a. Applicant is attempting to change the priority of the application after prosecution is closed.
 - b. The deletion of "substantially crystalline" from claim 7 is improper broadening after prosecution is closed.
 - c. The new specification includes a line repeat beginning on page 24, last line and extending through page 25, second line.
2. The drawings filed January 4, 2002 are acceptable and have been entered.
3. The application will be forwarded to Publications for preparation for Patent issuance.

Any inquiry concerning this communication or earlier communications from the examiner should be directed to Terrel Morris whose telephone number is 703-308-2414.

The fax phone number for the organization where this application or proceeding is assigned is (703) 872-9310. Any inquiry of a general nature or relating to the status of this application or proceeding should be directed to the receptionist whose telephone number is (703) 308-0661.



Terrel Morris
Supervisory Patent Examiner
Group Art Unit 1771



MARKED-UP COPY OF
SPECIFICATION AND CLAIMS

RECEIVED

MAY 21 2001

TC 1700

APPLICATION FOR LETTERS PATENT

Be it known that Takehiko Sumi, a citizen of Japan, having a residence address at 23-1, Kamiimaizumi, 4-Chome, Ebina-Shi, Kanagawa 243-0431 Japan, and Tetuya Fukumoto a citizen of Japan having a residence address at 1205, Shimowada, Yamato-Shi, Kanagawa 242-0015 Japan, have invented a new and useful method and article of manufacture, a MOLDED ARTICLE LAMINATED WITH FABRIC AND METHOD FOR REPROCESSING THE SAME of which the following is a specification therefor.

MOLDED ARTICLE LAMINATED WITH FABRIC AND
METHOD FOR REPROCESSING THE SAME

5

CROSS REFERENCE TO RELATED APPLICATIONS

This application claims priority under 35 U.S.C. §119 from a Japanese Patent Application No. 9-369501 filed on December 26, 1997, which is incorporated herein by reference for all purposes.

10

BACKGROUND OF THE INVENTION

TECHNICAL FIELD OF THE INVENTION

The present invention relates to a molded article laminated with fabric which is prepared
15 by adhering a fabric made up of highly heat resisting fibers to the surface of a molding produced from a thermoplastic resin and to a method for reprocessing the molded article laminated with fabric.

Plastic moldings, which are used in such applications as inner walls, partitions and doors
20 of buildings, and head rests, arm rests and solid portions of console boxes of automobiles and which are molded articles laminated with fabric, are described in Japanese Patent Application Publication (JP-B) No. 63-51,088.

In the case of the molded articles laminated with fabric described in JP-B No. 63-51,088,
25 as will be seen in FIG. 1, a fiber sheet is present in part of the mold flash when the molding is prepared. Generally, mold flashes which contain no fiber sheet are reprocessed without any treatment. The mold flashes and defective moldings which contain a fiber sheet are actually discarded without being reused. This is because the residual fiber sheet brings about the problem that the difference in bulk density between fibrous portions and the resinous portions causes
30 nonuniformity in the charging amount to an extruder thereby making the extruded amount

unstable. In addition, the reuse of the mold flashes containing a fiber sheet brings about the problem that fibrous lumps remain on the surface of the moldings obtained thereby impairing the appearance and significantly reducing the physical strength of the moldings.

5 Accordingly, for the preparation of a mold article laminated with fabric, the mold structure needs to be designed so that the amount of mold flashes is minimized. Despite such precaution in designing, however, fiber sheets needs to be carefully removed manually if the mold flashes containing the fiber sheets are reused.

10 In view of the actual situation where a large amount of molded articles laminated with fabric are widely used in the field of automobile industry, construction industry and the like, it is extremely difficult to manually remove the fiber sheets from the mold flashes in terms of productivity. Therefore, it is an inevitable consequence that the mold flashes are forced to be discarded in the face of the fact that the recycling of plastics is strongly encouraged.

15

SUMMARY OF THE INVENTION

 Accordingly, an object of the present invention is to provide a method not only for reprocessing the mold flashes at the time of the preparation of molded articles laminated with
20 fabric but also for reprocessing the defective molded articles laminated with fabric which come from the production line and are destined to be discarded.

 Another object of the present invention is to provide a method which makes it possible to prevent the impairment of the physical properties and appearance of the moldings prepared by
25 reusing the resinous material containing the fiber sheets and which enables accurate control of the parameters, such as wall thickness of the moldings, in the forming process.

 The molded article laminated with fabric according to the present invention is a molding which is made from a thermoplastic resin (A) and has a fabric, made up of fibers of a highly heat
30 resisting thermoplastic resin (B), adhered to the surface thereof, wherein the thermoplastic resin

(A) of the molding contains the highly heat resisting thermoplastic resin (B) constituting the fibers and wherein the highly heat resisting thermoplastic resin (B) is present as ~~minute particles~~ a microdispersion in the thermoplastic resin (A). The minute particles of the microdispersion of typically only a few microns in diameter, which is not possible with prior art processes. In a preferred embodiment the volume average of the minute particles is 10 microns or less. In the molded article laminated with fabric of the present invention, it is desirable that the content of the highly heat resisting thermoplastic resin (B) in the thermoplastic resin (A) does not exceed 20% by weight.

The method for reprocessing moldings according to the present invention relates to a method for reprocessing a molded article laminated with fabric which is made from a thermoplastic resin (A) and has a fabric, made up of fibers of a highly heat resisting thermoplastic resin (B), adhered to the surface thereof, wherein the method comprises charging an extruder with a crushed product obtained by finely crushing the molded article laminated with fabric, melt-blending the crushed product at a temperature, which is within the range of from the melting point to a temperature 50°C higher than the melting point of the highly heat resisting thermoplastic resin (B) constituting the fibers, to thereby produce a blend resin, and extruding the blend resin from the extruder to thereby granulate the blend resin.

resin. The thermoplastic resin (B) in the form of large islands is converted into a microdispersion by blending in the extruder and extruding the blend from the extruder. That is, the melt-blending by means of an extruder converts the resin present in the form of large islands into a microdispersion of minute particles. The size of the minute particles is less than 10 microns, but is approximately 1 micron in a preferred embodiment. Because of this microdispersion, even if the thermoplastic resin (A) is separated from the thermoplastic resin (B) at the interface thereof, the separation is very minute and therefore the basic physical properties of the thermoplastic resin (A) are hardly influenced by the separation.

Conditions suited for the implementation of the method for reprocessing a molding according to the present invention are as follow. The melt-blending temperature is within the range of from the melting point to a temperature 30°C higher than the melting point of the highly

heat resisting resin constituting the fibers. The melt-blending time is 20 to 600 seconds. The thermoplastic resin (A) is a polyolefinic resin, such as high-density polyethylene or polypropylene, a polystyrene resin, an ABS resin, a modified polyphenylene ether, or the like. The thermoplastic resin (B) is nylon or polyester.

5

In the case of a crystalline thermoplastic resin, the melting point as referred to in the present invention is a melting point measured by differential scanning calorimetry. In the case of a noncrystalline thermoplastic resin, the melting point is referred to in the present invention as a flow-starting temperature (a temperature at which a flow of 2 mm³/second is attained under a condition using a load of 100 Kg and a die having a diameter of 1 mm and a length of 10 mm) when measured by means of a flow tester in which the resin flows down.

10

Still other objects and advantages of the present invention will become readily apparent to those skilled in this art from the following detailed description, wherein only a preferred embodiment of the invention is described, simply by way of illustration of the best mode contemplated for carrying out the invention. As will be realized, the invention is capable of other and different embodiments, and its several details are capable of modifications in various obvious respects, all without departing from the invention.

15

20

BRIEF DESCRIPTION OF THE DRAWINGS

The present invention will be readily understood by the following detailed description in conjunction with the accompanying drawings, wherein like reference numerals designate like structural elements, and in which:

FIG. 1 is an oblique view illustrating the molded article laminated with fabric of the present invention.

FIG. 2 is a diagram illustrating a state where a parison and a fiber sheet are disposed between mold halves in accordance with the method of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT

As shown in FIG.1, the molded article laminated with fabric 1 has a hollow double-wall structure in which the surface of the molding 2 has a fabric 3 comprising a fiber sheet adhered thereto. The thermoplastic resin (A), which constitutes the molding 2, is a resin whose melting point is lower than that of the thermoplastic resin (B) constituting the fibers. Examples of the thermoplastic resin (A) include high-density polyethylene, polypropylene, polystyrene resins, polyamide resins, soft polyvinyl chloride resins, hard polyvinyl chloride resins, ABS resins, AS resins, AES resins, and ASA resins as well as polyethylene terephthalate resins, polybutylene terephthalate resins, modified polyphenylene ethers, and elastomers, such as polyurethane elastomers, polystyrene elastomers, polyolefin elastomers, polyamide elastomers, and polyester elastomers, each having a lower melting point in the range of from 150 to 245°C.

Examples of the fiber sheet, which constitutes the fabric 3, include a cloth, a knitting and a nonwoven fabric which are each obtained by processing synthetic fibers, such as polyamide, e.g., nylon 6 or nylon 66, polyester, and the like, blends of these synthetic fibers, or blend fibers comprising such synthetic fibers and 20% or less of other fibers (e.g., natural fibers such as cotton, hemp, wool and silk, regenerated fibers such as viscose rayon and cupro-ammonium rayon, semi-synthetic fibers such as acetate and triacetate, and synthetic fibers such as acrylic, vinylon, polypropylene and polyurethane).

The molded article laminated with fabric 1, which is shown in FIG. 1, is obtained by a process comprising disposing a parison 6, which is extruded from an extrusion head 5, and a fabric 3 between mold halves 4 and effecting blow-molding so that the fabric 3 adheres to the surface of the molding 2, as shown in FIG. 2.

In the prior art, when a thermoplastic resin having a fiber sheet adhered thereto is crushed in a crusher, the fiber sheet is cut into appropriate lengths thereby providing fibrous lumps having a size of several millimeters to tens of millimeters. Since the melting temperature of these fibrous lumps differs from that of the thermoplastic resin, which constitutes the molding to be

prepared by blow-molding and which has a lower melting point, a molding produced from the blend of the fibrous lumps and the thermoplastic resin has a poor appearance because of the emergence of the fibers on the surface of the molding. In addition, the desired strength as a molding cannot be obtained because the fibers are basically infusible and remain in the form of the fibers themselves.

The present invention overcomes these problems, and provides a defect free appearance with sufficient strength. A general explanation of the process is described herein, although other embodiments are within the scope of the invention.

In one embodiment, the thermoplastic resin (A) constituting the molding is polypropylene and the highly heat resisting thermoplastic resin (B) constituting the fabric is a polyester resin (polyethylene terephthalate). According to the present invention, moldings or flashes having a fabric adhered thereto are crushed in a crusher. In this case, the polyester resin constituting the fabric is in the form of aggregates of fibers cut into a certain length and the aggregates are mixed with the crushed product of the polypropylene constituting the molding. The crushed product of polypropylene which constitutes the molding and the polyester resin in the form of fibrous lumps are charged into an extruder and are kept at a temperature above the melting point of the polyester resin for a certain period of time. This treatment melts the fibrous lumps of the polyester resin and converts them into resinous lumps because the polyester resin is brought to a temperature above the melting temperature thereof.

Suppose the lumps of the polyester and the crushed polypropylene are not blended by means of a screw. The lumps made up of molten polyester resin are believed to be in the form of large islands in the polypropylene which constitutes the molding. That is to say, the polyester resin is believed to be present as large islands in the polypropylene presenting the form of foam of sea after being melted.

In addition, if the polypropylene and the polyester resin in the form of fibrous lumps are kept at a temperature which is 50°C higher than the melting point of the polyester resin, thermal

degradation of the plastics takes place thereby exhibiting a remarkable impairment of the physical properties.

Generally, a polyester resin is not compatible with a polypropylene resin, and therefore these resins are not miscible with each other. Therefore, the state, where the polyester resin is present as large islands in the polypropylene presenting the ~~form~~foam of sea, results in a molding with a lessened mechanical strength. This is because even a very small external force easily separates the polypropylene resin from the polyester resin at the interface thereof.

In order to overcome this problem, according to the present invention, the polyester resin in the form of large islands is converted into a microdispersion by blending in an extruder and extruding the blend from the extruder. That is, the melt-blending by means of an extruder can convert the polyester resin present in the form of large islands into a microdispersion of minute particles. The size of the minute particles is 10 microns or less on average. Because of this microdispersion, even if the polypropylene resin is separated from the polyester resin at the interface thereof, the separation is very minute and therefore the basic physical properties of the polypropylene are hardly influenced by the separation.

Accordingly, the present invention does not increase the rigidity by increasing the compatibility between the two components. Since the polyester resin is dispersed in the state of minute particles, the presence of the polyester exerts almost no influence on the basic physical properties of the polypropylene as a whole. Because of this, no additive or filler is needed for the purpose of the compatibilization. Use of a conventional extruder brings about the desired result.

The extruder in the present invention may be a single-screw extruder or a twin-screw extruder.

An extruder which exhibits an excellent blending performance is particularly preferred.

Although a twin-screw extruder is known to exhibit an excellent blending performance, a single-screw extruder provided with a high-performance blending section, such as Maddox screw with flutes, Dalmage screw, or double-flight screw, is known. Another suitable single-screw extruder is, for example, a two-stage extruder in which screws are exchanged midway.

The blend resin, which is obtained by the above-described method of the present invention, can be satisfactorily used again for molding, such as blow molding, injection molding, or the like, by a conventional molding machine. Naturally, however, the molding temperature is a temperature suited for the molding of polypropylene (generally in the range of from 170 to 220°C) in the case where polypropylene is used as described above, because at this temperature, the polyester does not melt. Therefore, when molded in this way, the polyester resin constituting the fabric is present in an unmelted state as in the case of a traditional molding operation. The resultant defect free article is derived from the present invention despite the fact that the polyester resin remains unmelted as in the case of a traditional molding operation. This defect free process is based on the phenomenon that the polyester resin is present in a state of microdispersion. If the polyester resin in the state of fibrous lumps is melted and dispersed by means of an extruder, the fibrous lumps of the polyester resin is converted into particles which, even if unmelted, acts as a filler and contributes to the improvement of the rigidity. It is known that if a certain amount of a filler, such as mica or talc, is incorporated into a thermoplastic resin, the physical properties such as rigidity of the molding made from the thermoplastic resin are improved. This type of filler is not in a molten state in the molten thermoplastic resin. The contribution to the improvement of the physical properties, such as rigidity, of the molding is due to the very microdispersion of the filler. The resin, which constitutes the fibers in the present invention and which is exemplified by the polyester resin, is not in a molten state in the molten polypropylene resin. The improvement of the rigidity is obtained because the polyester resin is present as minute particles and is dispersed in the polypropylene resin.

Further, according to the present invention, the blend resin, after being melted by dispersing the fibrous lumps by melt-blending, is extruded in the shape of strands which are then cut into pellets, or otherwise extruded in the shape of blocks which are then crushed by means of a crusher. In this way, the blend resin is granulated. The granules thus obtained are blended with a virgin resin or a regenerated resin which is in a crushed state and does not contain fibrous lumps. The resulting blend is subjected to a molding operation, such as blow molding, injection molding, extrusion molding, or the like, and thus recycling is performed. In the present invention, since the blend resin is granulated, the granules can be charged into the molding

machine in a stable manner. Since the bulk density of the granules of the blend resin is similar to that of the virgin resin, these resins can be charged into the molding machine uniformly.

As stated above, the method for reprocessing according to the present invention makes it possible to reuse the mold flashes of the molded articles laminated with fabric or the defective portions of the molded articles laminated with fabric which have been hitherto discarded.

Further, since the method for reprocessing according to the present invention makes it possible to process all of the fabric adhered to the moldings so that the fabric is mingled in new moldings, the method is useful and advantageous to environments.

When the granules thus obtained are blended with a virgin resin, a regenerated resin, which is in a crushed state and does not contain fibrous lumps, or a blend of these resins, so as to produce moldings, the moldings produced in this way are not limited to molded articles laminated with fabric and naturally include moldings without the fabric adhered thereto.

EXAMPLES

The following examples are illustrative of the present invention and are not limiting mechanisms of the scope of the present invention. Resins used in a preferred embodiment include:

EC9 Polypropylene (hereinafter referred to as PP) manufactured by Nippon Polychem Co., Ltd., with a melting point of 162°C.

B-871 Polyethylene (hereinafter referred to as PE) manufactured by Asahi Chemical Industry Co., Ltd., with a melting point of 128°C.

The fiber sheets of the preferred embodiment are a needle punched carpet, which was made up of polyester fibers having a melting point of 255°C (hereinafter referred to a carpet A), and a tufted carpet, which was made up of cut pile of nylon 6 fibers having a melting point of 223°C and a base fabric of polypropylene fibers having a melting point of 162°C (hereinafter

referred to as carpet B), were used. In the carpet B, the weight ratio of the nylon fibers to the polypropylene fibers was 3:1.

The extruder of the preferred embodiment, TEM75, was manufactured by Toshiba Machine Co., Ltd. The screw diameter of this extruder was 75 mm and the motor had a power of 185 KW.

	Plastics	Cloth
Example 1	PP	Carpet A
Example 2	PP	Carpet B
Example 3	PE	Carpet A
Example 4	PE	Carpet B
Example 5	PP	Carpet A

TABLE I

Example 1

The molded article laminated with fabric as shown in FIG. 1 was prepared by a blow-molding operation using PP as the thermoplastic resin (A) and the carpet A as the fabric. The machine used for the blow molding operation was a molding machine which had a screw diameter of 90 mm and an L/D ratio of screw of 24 and which was manufactured by Nippon Steel Work Corp. The resin temperature of PP was about 200°C and the blowing pressure was about 7 Kg/cm².

After blow molding, the peripheral flashes formed were separated into portions having the fabric adhered thereto and portions having no fabric. Then, only the portions having the fabric adhered thereto were crushed in a crusher so as to obtain crushed product consisting of cubes whose sides were each about 7 mm long. The crushed product contained both cloth and resin, wherein the weight ratio of the resin to the cloth was 90:10.

The crushed product was charged into the hopper of the TEM 75 extruder manufactured by Toshiba Machine Co., Ltd., wherein the temperature of the extruder was set to the temperatures shown in Tables 2 and 3 and the crushed product was kept in the extruder for retention times shown in Tables 2 and 3. The crushed product was extruded from the head at the tip of the extruder so as to obtain strand-shaped resin having a diameter with cross-sectional area of about 3 mm. The strand was then cut into pellets, each having a length of 5 mm.

The pellets and virgin PP were blended so as to prepare a blend comprising 80% of the virgin PP and 20% of the pellets. The blend was charged into the single-screw extruder, wherein the resin temperature was set to 200°C. In this condition, a blow-molding operation was performed by using the mold, and thus a molded article laminated with fabric was obtained. In this case, the content of the fibrous resin was 2%. For the purpose of the evaluation of the molding thus obtained, the appearance was visually inspected and reduction in strength was examined by means of a tensile test (in accordance with JIS K 7113).

In the evaluation of the appearance the following symbols are used:

DF = a defect-free article;

SD = a slightly defective article having, for example, localized unmelted portions or excessively thin walls; and

MD = an article having a molding defect.

In the test of strength, the following symbols are utilized:

DF = the absence of reduction in tensile strength;

SR = a slight reduction in tensile strength; and

RR = a remarkable reduction in tensile strength.

Example	Temperature (°C)	Time (sec)	Recycled Pellet %	Virgin Pellet %	Evaluation	
					Appearance	Strength
Example 1 - 1	200	180	20	80	MD	RR
Example 1 - 2	230	180	20	80	MD	RR
Example 1 - 3	245	180	20	80	MD	RR
Example 1 - 4	255	180	20	80	DF	DF
Example 1 - 5	265	180	20	80	DF	DF
Example 1 - 6	275	180	20	80	DF	DF
Example 1 - 7	285	180	20	80	DF	DF
Example 1 - 8	300	180	20	80	DF	DF
Example 1 - 9	315	180	20	80	DF	RR
Example 1 - 10	275	15	20	80	SD	SR
Example 1 - 11	275	20	20	80	DF	DF
Example 1 - 12	275	300	20	80	DF	DF
Example 1 - 13	275	600	20	80	DF	DF
Example 1 - 14	275	700	20	80	DF	RR

Table 2

It can be seen that defect-free articles can be obtained if the temperature for the formation of pellets is in the range of from 255 to 300°C (Example 1-4~Example 1-8). If the retention time is 180 seconds for the formation of pellets, the temperature is preferably is in the range of from 265 to 285°C (Example 1-5~Example 1-7).

If the temperature for the formation of pellets is 245°C or below, defective appearance emerges (Example 1-1~Example 1-3). If the temperature for the formation of pellets is above 300°C, the productivity in pellet production becomes worse and the physical properties of the moldings obtained become inferior.

It can be seen that proper time for melting for the formation of pellets is in the range of from 20 to 600 seconds if the temperature is 275°C. If the time is 15 seconds, unmelted portions are present, whereas pelletization was impossible if the time was 700 seconds.

5

If the time was 700 seconds, the extrudate had a very low viscosity and was in the state of syrup. Because of this low viscosity, the extrudate could not be pulled to a pelletizer, and therefore the pelletization was impossible. The substance in the state of syrup was crushed and the crushed product was subjected to the same blow-molding operation. The strength of the molding thus obtained was then subjected to a test of tensile strength, and it was found that the physical properties of this molding were remarkably inferior.

10

Example 2

The procedure of Example 1 was repeated, except that the carpet A as used therein was replaced with the carpet B. The content of the fibrous resin was 2% by weight.

15

In the evaluation of the appearance the following symbols are used:

DF = a defect-free article;

20

SD = a slightly defective article having, for example, localized unmelted portions or excessively thin walls; and

MD = an article having a molding defect.

In the test of strength, the following symbols are utilized:

DF = the absence of reduction in tensile strength;

25

SR = a slight reduction in tensile strength; and

RR = a remarkable reduction in tensile strength.

30

Example	Temperature (°C)	Time (sec)	Recycled Pellet %	Virgin Pellet %	Evaluation	
					Appearance	Strength
Example 2 - 1	200	180	20	80	MD	RR
Example 2 - 2	215	180	20	80	MD	RR
Example 2 - 3	225	180	20	80	SD	DF
Example 2 - 4	235	180	20	80	DF	DF
Example 2 - 5	245	180	20	80	DF	DF
Example 2 - 6	255	180	20	80	DF	DF
Example 2 - 7	265	180	20	80	DF	DF
Example 2 - 8	275	180	20	80	DF	DF
Example 2 - 9	285	180	20	80	DF	DF
Example 2 - 10	300	180	20	80	DF	DF
Example 2 - 11	310	180	20	80	DF	RR
Example 2 - 12	255	15	20	80	SD	SR
Example 2 - 13	255	20	20	80	DF	DF
Example 2 - 14	255	300	20	80	DF	DF
Example 2 - 15	255	600	20	80	DF	DF
Example 2 - 16	255	700	20	80	DF	RR

Table 3

It can be seen that defect-free articles can be obtained if the temperature for the formation of pellets is in the range of from 235 to 300°C (Example 2-4~Example 2-10). If the retention time is 180 seconds for the formation of pellets, the temperature is preferably in the range of from 235 to 265°C (Example 2-4~Example 2-7).

If the temperature for the formation of pellets is 225°C or below, defective appearance emerges (Example 2-1~Example 2-3). If the temperature for the formation of pellets is above 300°C, pelletization was impossible.

5 If the temperature for the formation of pellets was above 300°C, the extrudate had a very low viscosity and was in the state of syrup. Because of this low viscosity, the extrudate could not be pulled to a pelletizer, and therefore the pelletization was impossible. The substance in the state of syrup was crushed and the crushed product was subjected to the same blow-molding operation. The strength of the molding thus obtained was then subjected to a test of tensile
10 strength, and it was found that the physical properties of this molding were remarkably inferior.

It can be seen that proper time for melting for the formation of pellets is in the range of from 20 to 600 seconds if the temperature is 255°C. If the time is 15 seconds, unmelted portions are present, whereas, if the time is 700 seconds or more, the time is too long and the productivity
15 in pellet production is poor. In addition, the physical properties of the moldings are inferior.

Example 3

The procedure of Example 1 was repeated, except that PP as used therein was replaced with PE. The content of the fibrous resin was 2% by weight.

20 In the evaluation of the appearance the following symbols are used:

DF = a defect-free article;

SD = a slightly defective article having, for example, localized unmelted portions or excessively thin walls; and

25 MD = an article having a molding defect.

In the test of strength, the following symbols are utilized:

DF = the absence of reduction in tensile strength;

SR = a slight reduction in tensile strength; and

RR = a remarkable reduction in tensile strength.

30

Example	Temperature (°C)	Time (sec)	Recycled Pellet %	Virgin Pellet %	Evaluation	
					Appearance	Strength
Example 3 - 1	200	180	20	80	MD	RR
Example 3 - 2	230	180	20	80	MD	RR
Example 3 - 3	245	180	20	80	MD	RR
Example 3 - 4	255	180	20	80	DF	DF
Example 3 - 5	265	180	20	80	DF	DF
Example 3 - 6	275	180	20	80	DF	DF
Example 3 - 7	285	180	20	80	DF	DF
Example 3 - 8	300	180	20	80	DF	DF
Example 3 - 9	315	180	20	80	DF	RR
Example 3 - 10	275	15	20	80	SD	SR
Example 3 - 11	275	20	20	80	DF	DF
Example 3 - 12	275	270	20	80	DF	DF
Example 3 - 13	275	600	20	80	DF	DF
Example 3 - 14	275	700	20	80	DF	RR

Table 4

It can be seen that defect-free articles can be obtained if the temperature for the formation of pellets is in the range of from 255 to 300°C (Example 3-4~Example 3-8). If the retention time is 180 seconds for the formation of pellets, the temperature is preferably is in the range of from 265 to 285°C (Example 3-5~Example 3-7). If the temperature for the formation of pellets is 245°C or below, defective appearance emerges (Example 3-1~Example 3-3).

It can be seen that proper time for melting for the formation of pellets is in the range of from 20 to 600 seconds if the temperature is 275°C. If the time is 15 seconds, unmelted portions are present, whereas, if the time is 700 seconds or more, the time is too long and the productivity

in pellet production is poor. In addition, the physical properties of the moldings thus obtained are inferior.

Example 4

- 5 The procedure of Example 2 was repeated, except that PP as used therein was replaced with PE. The content of the fibrous resin was 2% by weight.

In the evaluation of the appearance the following symbols are used:

- DF = a defect-free article;
 10 SD = a slightly defective article having, for example, localized unmelted portions or excessively thin walls; and
 MD = an article having a molding defect.

In the test of strength, the following symbols are utilized:

- 15 DF = the absence of reduction in tensile strength;
 SR = a slight reduction in tensile strength; and
 RR = a remarkable reduction in tensile strength.

Example	Temperature (°C)	Time (sec)	Recycled Pellet %	Virgin Pellet %	Evaluation	
					Appearance	Strength
Example 4 - 1	200	180	20	80	MD	RR
Example 4 - 2	215	180	20	80	MD	RR
Example 4 - 3	225	180	20	80	SD	DF
Example 4 - 4	235	180	20	80	DF	DF
Example 4 - 5	265	180	20	80	DF	DF
Example 4 - 6	285	180	20	80	DF	DF
Example 4 - 7	300	180	20	80	DF	DF
Example 4 - 8	310	180	20	80	DF	RR

Example 4 - 9	325	180	20	80	DF	RR
Example 4 - 10	285	15	20	80	SD	SR
Example 4 - 11	285	20	20	80	DF	DF
Example 4 - 12	285	300	20	80	DF	DF
Example 4 - 13	285	600	20	80	DF	DF
Example 4 - 14	285	700	20	80	DF	RR

Table 5

It can be seen that defect-free articles can be obtained if the temperature for the formation of pellets is in the range of from 235 to 300°C (Example 4-4~Example 4-7). If the retention time is 180 seconds for the formation of pellets, the temperature is preferably in the range of from 235 to 265°C (Example 4-4~Example 4-5). If the temperature for the formation of pellets is 225°C or below, defective appearance emerges (Example 4-1~Example 4-3).

It can be seen that proper time for melting for the formation of pellets is in the range of from 20 to 600 seconds if the temperature is 285°C. If the time is 15 seconds, unmelted portions are present, whereas, if the time is 700 seconds or more, the time is too long and the productivity in pellet production is poor. In addition, the physical properties of the moldings thus obtained are inferior.

Example 5

The procedure of Example 1 was repeated, except that the weight of the fabric for the preparation of molded article laminated with fabric by blow molding was increased so that the ratio of the resin to the fabric in the crushed product was 70:30. The pellets obtained were each blended with a virgin material at the following ratios and respective blow-molded articles were obtained. The blending ratios for the recycled pellets were 40% by weight, 50% by weight, 60% by weight, 70% by weight, 80% by weight, 90% by weight and 100% by weight; and wherein the contents of the fibrous resin were 12% by weight, 15% by weight, 18% by weight, 21% by

weight, 24% by weight, 27% by weight and 30% by weight, respectively.

In the evaluation of the appearance the following symbols are used:

DF = a defect-free article;

5 SD = a slightly defective article having, for example, localized unmelted portions or excessively thin walls; and

MD = an article having a molding defect.

In the test of strength, the following symbols are utilized:

DF = the absence of reduction in tensile strength;

10 SR = a slight reduction in tensile strength; and

RR = a remarkable reduction in tensile strength.

Example	Temperature (°C)	Time (sec)	Recycled Pellet %	Virgin Pellet %	Fibrous Resin %	Evaluation	
						Appearance	Strength
Example 5 - 1	275	180	40	60	12	DF	DF
Example 5 - 2	275	180	50	50	15	DF	DF
Example 5 - 3	275	180	60	40	18	DF	DF
Example 5 - 4	275	180	70	30	21	SD	DF
Example 5 - 5	275	180	80	20	24	MD	SR
Example 5 - 6	275	180	90	10	27	MD	SR
Example 5 - 7	275	180	100	0	30	MD	SR

Table 6

15 It can be seen that defect-free articles can be obtained if the contents of the fibrous resin in the molding are up to 20% by weight (Example 5-1~Example 5-3).

The objects and advantages of the present invention may be further realized and attained by means of the instrumentalities and combinations particularly pointed out in the appended claims.

20 Accordingly, the drawing and description are to be regarded as illustrative in nature, and not as

KY81

restrictive.

CLAIMS

WHAT IS CLAIMED IS:

28. (Once Amended) A molded hollow article laminated with fabric, comprising:
5 a thermoplastic resin (A) with a microdispersion of a highly heat resistant thermoplastic resin (B), wherein said microdispersion is a melt-blending of minute particles of said highly heat resistant thermoplastic resin (B) within said thermoplastic resin (A);
(A), and wherein said minute particles have a volume average diameter of 10 microns or less; and
10 a fabric adhered to a surface of said thermoplastic resin (A), wherein said fabric comprises fibers of said highly heat resistant thermoplastic resin (B).
29. A molded hollow article laminated with fabric according to claim 28, wherein said thermoplastic resin (A) is selected from the group consisting of a high-density
15 polyethylene, polypropylene, polystyrene resin, ABS resin, and modified polyphenylene ether.
30. A molded hollow article laminated with fabric according to claim 28, wherein said highly
20 heat resistant thermoplastic resin (B) is selected from the group consisting of nylon and polyester.
31. A molded hollow article laminated with fabric according to claim 28, wherein said molded article is produced by blow molding.
- 25 32. A molded hollow article laminated with fabric according to claim 28, wherein said microdispersion of said highly heat resistant thermoplastic resin (B) in the thermoplastic resin (A) does not exceed 20% by weight.
- 30 33. (Once Amended) A molded article laminated with fabric produced by a process of:
melt-blending a thermoplastic resin (A) with a microdispersion of a highly heat resistant

thermoplastic resin (B) to produce a blend resin, wherein said microdispersion is minute particles having a volume average diameter of 10 microns or less of said highly heat resistant thermoplastic resin (B) , and wherein said step of melt-blending is done at a
 5 temperature that ranges from the melting point of said highly heat resistant thermoplastic resin (B) to a temperature 30°C higher than the melting point of said highly heat resistant thermoplastic resin (B); and
 molding said blend resin with a fabric, wherein said fabric has fibers of said highly heat resistant thermoplastic resin (B).

10 34. Canceled herein

35. A molded article laminated with fabric according to claim 33, wherein~~34. A molded article laminated with fabric according to claim 33, wherein~~
~~35. A molded article laminated with fabric according to claim 33, wherein said microdispersion of said highly~~
 15 ~~heat resistant thermoplastic resin (B) in the thermoplastic resin (A) does not exceed 20% by weight.~~

the blending time is between 20 to 600 seconds.

20 36. A molded article laminated with fabric according to claim 33, wherein said ~~blending is done in an extruder.~~

~~37. A molded article laminated with fabric according to claim 33, wherein said thermoplastic resin (A) with a microdispersion of a highly heat resistant thermoplastic resin (B) is~~
 25 ~~obtained from reprocessing moldings.~~

30

ABSTRACT OF THE DISCLOSURE

~~The present invention relates to a molded article laminated with fabric wherein a thermoplastic resin (A) has a fabric, made up of fibers of a highly heat resisting thermoplastic resin (B), adhered to the surface thereof, wherein the thermoplastic resin (A) of the molding contains the highly heat resisting thermoplastic resin (B) constituting the fibers and wherein the highly heat resisting thermoplastic resin (B) is present as minute particles in the thermoplastic resin (A), and a method not only for reprocessing the mold flashes at the time of the preparation of molded articles laminated with fabric but also for reprocessing the defective molded articles laminated with fabric which come from the production line and are destined to be discarded.~~

microdispersion of said highly heat resistant thermoplastic resin (B) in the thermoplastic resin (A) does not exceed 20% by weight.

37. A molded article laminated with fabric according to claim 33, wherein said blending is done in an extruder.

38. A molded article laminated with fabric according to claim 33, wherein said thermoplastic resin (A) with a microdispersion of a highly heat resistant thermoplastic resin (B) is obtained from reprocessing moldings.

ABSTRACT OF THE DISCLOSURE

5 The present invention relates to a molded article laminated with fabric wherein a
thermoplastic resin (A) has a fabric, made up of fibers of a highly heat resisting thermoplastic
resin (B), adhered to the surface thereof, wherein the thermoplastic resin (A) of the molding
contains the highly heat resisting thermoplastic resin (B) constituting the fibers and wherein the
highly heat resisting thermoplastic resin (B) is present as a microdispersion in the thermoplastic
resin (A), and a method not only for reprocessing the mold flashes at the time of the preparation
of molded articles laminated with fabric but also for reprocessing the defective molded articles
10 laminated with fabric which come from the production line and are destined to be discarded.